

FLOMO PLASTICS INDUSTRIAL CO., LTD.

No. 42, Sec. 2 Zhongshan Road, Hu Nei District, Kaohsiung, Taiwan

The following merchandise was submitted and identified by the applicant as:

Product Description: EW100 ERASER

We have tested the submitted sample(s) as requested and the following results were obtained:

Test Requested: Aqueous Extractable Protein


Test Method: Refer to ASTM D5712-15 Analysis of Aqueous Extractable Protein in Natural Rubber and Its Products Using the Modified Lowry Method

Test Result: Please see attached pages.

Date of Receipt: AUG. 03, 2022

Testing Period: AUG. 04, 2022 ~ AUG. 24, 2022

Signed for and on behalf of
SGS Taiwan Ltd.



Tammy Wang
Supervisor



Test Result:

Test Equipment:

Name	Brand	Model
UV-VISIBLE Spectrophotometer	SHIMADZU	UV-1700

Lab. Environmental Conditions :

Ambient Temperature : (25 ± 3) °C

Relative humidity : (65 ± 10) %

Test Result:

Sample	Inspection Item	Result(s)
EW100 ERASER	Aqueous Extractable Protein (ppm)	n.d.

Note:

1. n.d. = not detected.
2. MDL(METHOD DETECTION LIMIT) : 0.2ppm.
3. The content of this report is invalid if it is not presented as the entire report.
4. The test was conducted at SGS Taiwan Ltd. Material and Engineering Laboratory-Kaohsiung.

– Picture(s) –




Photo A: Appearance of the sample

---End of Report---